Solution-processable Blue-Greenish Hybrid Polymeric/Perovskites Quantum Dots Light Emitting Diodes

Glaucio M. Santiago, José Carlos Germino, Jilian Nei de Freitas, Emre Yassitepe, Teresa D. Z. Atvars and Ana Flávia Nogueira

Abstract

In this present research the applicability of quantum dot (CsPbBr₃ perovskite) and polymer nanocomposites in LED were studied. Photophysical properties of the materials and the final hybrid LED were reached. The purpose of this material combination is the desirable properties mix of both.

Key words:

Perovskites, polymers, HLEDs

Introduction

Currently the organic electronic is growing, especially in light emitting diodes. This kind of material can be casted in flexible substrates.¹ The main problems in organic LEDs are low efficiency compared with inorganic ones. This failure can be avoided by adding inorganic materials with good luminescence, and preserving the processability in flexible substrates. In this scenario a new material aroused with promising properties.² The Cesium Lead Halide perovskites (CsPbX₃) have emission that depend on the halide (X), varying from the blue (chlorine) to red (Iode). This material can be processed in solution with a polymer to be casted in a substrate. In this current research was combined a polymer with CsPbBr₃ (green perovskite) in solution casted in films on a substrate to manufacture the devices.

Results and Discussion

It was fulfilled the photophysical measurements of different film conformation, all including a nanocomposite of quantum dots and polymer. At first the films were casted with quantum dots and Poly(9-vinylcarbazole) (PVK).

The absorbance in both CsPbBr₃ and PVK films are showed as peaks near of 290nm, more intensely in the perovskite one. Films with the nanocomposite have intermediate absorbance between QD and polymer. Making use of this data, the films were excited at 290nm and the fluorescence spectra were obtained.

Image 1. Photoluminescence of PVK, QD and nanocomposites at 290nm excitation.

It is seen that PVK presents emission in 407nm, while the typical perovskite emission is 521 nm. In the composite films as great as the proportion of perovskite was, the peak in 407nm had its intensity reduced and the quantum dot typical emission increased the intensity. Starting from 20% (w/w) of quantum dot in the film, the emission of PVK can

be considered negligible and perovskite appears strongly. The composite solutions were applied to fabricate the HLEDs, whose the composition is Glass|ITO|PEDOT:PSS|PVK:PQDs (% w/w)|Ca|Al

Image 2. Electroluminescence of HLEDs.

The electroluminescence spectra show about the same behavior of the photoluminescence. However, it seems that the PVK and CsPbBr₃ compete for charges, because PVK does not “disappear” as in photoluminescence. The results are not so pure spectra, nor blue neither green, which is expected for a only PVK or Quantum Dot LED, or with a complete energy transfer between the materials. The resume of optical-electronic properties of the PVK:PQDs composites HLEDs is shown below.

Chart 1. Optical-electronic properties of the PVK:PQDs composites HLEDs.

	$L_{\max}/\text{cd m}^{-2}$	$J/A \text{ cm}^{-2}$	$\eta_{\max}/\text{mcd A}^{-1}$
5.0 %	31.0	0.49	8.6
10.0 %	10.0	0.84	1.6
20.0 %	9.0	0.83	0.5
30.0 %	9.5	0.46	2.2

Conclusions

The HLEDs achieved in this research cannot be used in a emission of monochromatic light. The present HLEDs show a combination of blue and green emission that combined with a red emitting material can show a white emission.

Acknowledgement

The authors thank SAE, Fapesp, CNPq and Capes for financial support and fellowships.

¹ Akcelrud, L. Prog. Polym. Sci. **2003**, 28 (6), 875–962.

² Protesescu, L.; Yakunin, S.; Bodnarchuk, M. I.; Krieg, F.; Caputo, R.; Hendon, C. H.; Yang, R. X.; Walsh, A.; Kovalenko, M. V. Nano Lett. **2015**, 15 (6), pp 3692–3696.