Study of structural and magnetic properties presented by $Tb_{1-x}Pr_xNi_2$ compounds

Francesco Giuseppe Carotti*, Érik Oda Usuda, Adelino de Aguiar Coelho, Alexandre Magnus Gomes Carvalho

Abstract

On the search for better cores for cryogenic magnetic refrigeration, magnetic and structural properties, such as synchrotron x ray diffraction and magnetization of $Tb_{1-x}Pr_xNi_2$ were studied. The results show the linear behavior of the lattice parameter and the Curie temperature.

Key words:

Magnetism, Magnetocaloric effect, Structural properties

Introduction

This project was elaborated to evaluate the structural and magnetic properties of $Tb_{1-x}Pr_xNi_2$ compounds and its applications on cryogenic magnetic refrigeration. Magnetic refrigeration is based in the magnetocaloric effect, which consists in the material ability to change its temperature due to a variation on the applied magnetic field in an adiabatic process.

The lattice parameters of $TbNi_2$ ² and $PrNi_2$ ³ has, respectively, 0.056 Å and 0.053 Å difference from $Tb_{0.5}Pr_{0.5}Ni_2$ lattice parameter “a”. The curie temperature of $PrNi_2$ ⁴ is much lower than $TbNi_2$ ⁵, causing an abrupt fall as terbium is replaced by praseodymium. A fit of lattice parameters and curie temperatures shows that both of them vary linearly with x, $y = (-208 \pm 5)10^{-5}x + (13932 \pm 3)10^{-5}$ and $y = (-37 \pm 2)x + (38 \pm 1)$ describes the linear variation of the lattice parameters and the Curie temperatures, respectively.

Results and Discussion

For the preparation of the $Tb_{0.5}Pr_{0.5}Ni_2$ alloy, nickel 99.7%, praseodymium 99.9% and terbium 99.9% were melted in an arc furnace in an atmosphere of Ar. Then, synchrotron x ray diffraction data were collected to determinate the quality of the compound, based on Rietveld refinement¹. An analysis of the diffraction pattern peaks position done with Mathematica software presented $a = 7.2332 \pm 0.0001$ Å as the lattice parameter “a” of the compound. Later on, optical metallography showed that the compound presented 3 different phases identified as $Tb_{0.5}Pr_{0.5}Ni$, $Tb_{0.5}Pr_{0.5}Ni_2$ (majority phase) and $Tb_{0.5}Pr_{0.5}Ni_3$. Furthermore, magnetization thermal variation from 10 to 320 K at an applied magnetic field $H = 200$ Oe measurements were taken. Curie temperature $T_c = 20.5$ K was obtained analyzing the differential plot of the magnetization vs temperature.

Conclusions

It is possible to conclude that praseodymium rich alloys of $Tb_{1-x}Pr_xNi_2$ have a low Curie temperature, therefore better for cryogenic magnetic refrigeration. Also, the replacement of terbium by praseodymium causes an abrupt fall of nearly 40 K on the curie temperature, while the lattice parameter vary 0.109 Å, both of them with linear behavior.

Acknowledgement

We acknowledge financial support from CNPq – Conselho Nacional de Desenvolvimento Científico e Tecnológico – Brazil, and SAE Unicamp – Serviço de Apoio ao Estudante, Universidade Estadual de Campinas – Brazil and LNLS – Laboratório Nacional de Luz Síncrotron, Centro Nacional de Pesquisa em Energia e Materiais (CNPEM) – Brazil.

Image 1. Lattice parameter and curie temperature vs composition.

¹ H. Rietveld, J. Appl. Cryst. 2 (1969), 65 – 71.

² R.C. Mansey, G.V. Raynor and I.R. Harris, J. Less Com. Met. 14 (1968), 329-336.

³ E. Burzo, J. Laforest, Inter. J. Mag. 3 (1972), 171-177.

⁴ H. Mori, T. Fujita, T. Satoh and T. Ohtsuka, Phys. Letts. 79A (1980), 121-123

⁵ M.R. Ibarra, J.I. Arnaudas, P.A. Algarabel and A. del Moral, J. Magn. Magn. Mater. 46 (1984), 167-177.